

BASIC INFORMATION

PRODUCT NAME: FILAMENT 3D OneFIL3D PETG 1.75mm

PRODUCT DESCRIPTION: OneFIL3D PETG filament - poly(ethylene terephthalate) with addition of glycol and teflon in the form of a thread, designed for 3D printing using the FFF/FDM method. Filament coiled on spools or cardboard core (no spool), vacuum-packed with desiccant in a PA/PE bag, and then in a box. The product is designed for use with 3D printers using FDM technology. It should be used in a well ventilated room to avoid exposure to fume emissions during printing. It is important to avoid direct contact with hot printer components, which can lead to burns. Filament should be stored in a dry place, in a closed container and away from children. It is recommended to use the filament within the recommended printing temperature range for optimum results. Dispose of waste filament in accordance with local regulations. The product has been designed with safety in mind and meets all relevant standards for consumer use.

STORAGE: Store in dry area. Store in a closed container.

PRODUCT PARAMETERS

PARAMETER	VALUE
Filament diameter [mm]	1.75
Diameter tolerance [mm]	+/-0,05
Oval tolerance [mm]	+/-0,02

RECOMMENDED PRINTING PARAMETERS

PARAMETER	VALUE
3D printing temperature [C]	220-250
Heated bed [C]	60-80
Cooling fan [%]	0-60
3D printing temperature (High Speed printing) [C]	240-270
Closed chamber	not required
Drying conditions [C/h]	60/4

PHYSICAL PARAMETERS OF THE MATERIAL

PARAMETER	VALUE	UNIT	TEST METHOD
Gęstość /Density	1.29	g/cm ³	-
Moduł ugięcia/Flexural modulus	2100	MPa	ISO178
Naprężenie zginające przy zerwaniu/Flexural stress	70	MPa	ISO178
Naprężenie rozciągające przy zerwaniu/Tensile Stress at break	50	MPa	ISO527
Odkształcenie rozciągające przy zerwaniu /Tensile Strain at break	80	%	ISO527
Udarność wg metody Izoda (bez karbu)/Izod impact strength (unnotched)	5	kJ/m ²	ISO180/1A
Udarność wg metody Izoda (karb)/Izod impact strength (notched)	4,7	kJ/m ²	ISO180/1A
HDT	70	°C	ASTM D648
Klasa palności/Flammability rate	V2	-	UL 94

The values above have been measured using standard test specimens made of non-colored material at room temperature. The figures should be considered as indicative values only. Actual properties of OneFIL3D PETG parts can be affected by the printing parameters, design of the model, ambient conditions, application of the printout etc. It is essential that users test our products to determine whether they are suitable for their intended use. ROSA PLAST Sp. z o.o. accepts no liability for any health detriment or material losses or any other losses related to the use of the material. Additional documents, certificates and detailed technical information can be provided on special request.

